



Ultratop Loft W

One-component trowelable fine-grained cementitious paste applied in layers up to 2 mm thick to create decorative floors with a troweled or mottled effect

WHERE TO USE

Ultratop Loft W is the ideal coating product to create decorative interior floors and walls with a pronounced mottled effect.

Thanks to its ease of use, versatility and excellent resistance to abrasion, this product is ideal for creating floors subjected to intense pedestrian traffic in areas such as shops, restaurants, reception areas, private homes, cafes, hotels and showrooms, and generally in all areas relating to interior decorating in the residential and commercial building sector.

The consistency of the product, reduced thickness of the coat applied and the possibility of being applied also on vertical surfaces and of combining it with a various range of colours, allows an infinite variety of original and unique coatings to be created.

Some application examples

- Creating floors in shopping centres.
- Creating floors in residential areas.
- Creating coatings on floors, walls and ceilings with a troweled effect.
- Creating floors and walls in cafes and restaurants.
- Creating floors in wellness centres, hotel receptions and showrooms.
- In all areas in the residential and commercial building sector where a smooth and mottled effect with a cementitious matrix is required.

TECHNICAL CHARACTERISTICS

Ultratop Loft W is a powdered formulate made from special rapid setting and hydrating binders, graded silica sand, synthetic resin and special admixtures

according to a formulation developed in the MAPEI R&D laboratories.

When mixed with water it forms a non-self levelling, trowelable paste which is easy to apply by hand with a smooth Teflon-coated, rubber or steel trowel. The special colouring agent **Ultratop Color Paste** may be added to **Ultratop Loft W** during mixing to obtain an infinite variety of colours.

Also, thanks to the creamy consistency of the product, highly original decorative finishes may be obtained, such as classic troweled or mottled effects, in a multitude of shades.

Once hardened **Ultratop Loft W** has good resistance to abrasion.

ADVANTAGES

- Easy to prepare. Just mix with water and, if required, add special **Ultratop Color Paste** to get the colour required.
- Easy to apply by trowel and dries rapidly.
- Versatile: may be used for both new floors and to refurbish existing floors.
- It can be applied on both horizontal and vertical surfaces.
- Suitable for use in both commercial and residential areas.
- May be tinted with the special colouring agent **Ultratop Color Paste**.
- Treated surfaces are ready for use quickly.

RECOMMENDATIONS

- Do not apply **Ultratop Loft W** on dusty or crumbling

- surfaces or on surfaces with oil or grease stains.
- Do not add lime, cement, gypsum or other binders to **Ultratop Loft W**.
- Do not apply **Ultratop Loft W** on substrates with rising damp (contact MAPEI Technical Services Department).
- Do not apply **Ultratop Loft W** if the temperature is lower than +5°C or higher than +35°C.
- Do not apply **Ultratop Loft W** on exterior surfaces.
- Ultratop Color Paste** is the only product that can be used to colour **Ultratop Loft W**.

APPLICATION PROCEDURE

Preparation of the substrate

Substrates must be dry, solid and free of dust, loose and detached parts, paint, wax, oil, rust and any other substance which may affect adhesion.

It is very important that the surface is prepared according to specification to guarantee correct application and the best performance of **Ultratop Loft W**.

The most suitable method for preparing the surface is by grinding with a diamond disk and then removing all the dust with a vacuum cleaner. Do not use chemical preparation methods, such as acid rinsing, or aggressive percussion tools, to prevent damaging the substrate.

Repair defects, such as holes, pitting, cracking, etc., with **Eporip**, **Primer SN** or **Mapefloor I 300 SL**, depending on the width and depth of the defects and cracks.

If the substrate needs to be consolidated, use **Primer MF**.

Repair deep hollows or highly deteriorated areas on the surface of the floor with **Mapefloor EP19**, three-component epoxy mortar.

Reconstruct highly deteriorated joints using the same products.

If any of the above guidelines are not strictly adhered to, the quality of the final surface may be poor.

Priming the substrate

Horizontal surfaces

Following the mechanical preparation treatment, prime concrete and/or ceramic horizontal surfaces with **Primer SN** reinforced, where required, with **Mapenet 150** (glass fibre mesh) and blind with **Quartz 0.5**. Prepare **Primer SN** by pouring component B into component A and blend together with a drill with a spiral mixing attachment at low speed to form a smooth, even paste. While mixing, add approx. 20% by weight of **Quartz 0.5** to the paste as soon as it has been prepared and continue mixing for several minutes to form a smooth, even compound.

Pour the product onto the floor to be coated and spread it out evenly and uniformly using a smooth trowel or a smooth rake. While the product is still wet, blind the surface with **Quartz 0.5**.

Once **Primer SN** has hardened, remove excess sand with an industrial vacuum cleaner.

Vertical surfaces

Non-absorbent vertical surfaces (such as

ceramic, porcelain tiles, etc.), must be primed beforehand by applying a coat of **Primer Grip White** with a brush or a roller. Leave the primer to dry before applying **Ultratop Loft W**. Drying times depend on the surrounding conditions and absorbency of the substrate.

Treat absorbent vertical surfaces (concrete, render, skim coats and plaster-board walls), with a coat of **Primer LT**, a specific acrylic resin-based primer, diluted 1:1 or 1:2 by weight with water, depending on the absorbency of the substrate. Leave the primer to dry, depending on the surrounding conditions and absorbency of the substrate, before applying **Ultratop Loft W**.

Preparation of the product

Mix **Ultratop Loft W** with 32-35% by weight of clean water in a suitable container using an electric mixer at low speed to form a smooth, lump-free paste. If you wish to colour **Ultratop Loft W**, add the special **Ultratop Color Paste** to the mixing water and stir before adding and mixing into **Ultratop Loft W**.

Because of its high yield, we recommend preparing **Ultratop Loft W** in 5 kg batches.

Application of the product

Apply one or more coats of **Ultratop Loft W** with a smooth rubber, steel or Teflon-coated trowel scratching to zero thickness until the effect required is obtained.

In order to form a smooth, even finish, while leaving signs of the product formed by the trowelling motion still visible on the hardened surface, sand the surface of **Ultratop Loft W** between each coat and then after applying the final coat.

Wait until it is completely dry before sanding the surface between coats.

We recommend using a single-head sander with 80 to 200 grit sandpaper for this operation, depending on the effect required.

Finishing coat

6-24 hours after applying the final coat of **Ultratop Loft W** or **Ultratop Loft F** (it has to be dry), apply a finishing product from the **Mapefloor Finish** range to protect the surface and to make it non-absorbent. The most suitable finishing product must be chosen according to the aesthetic effect or level of wear-resistance required. Please contact the MAPEI Technical Services for information.

Cleaning

Remove **Ultratop Loft W** from tools with water while still fresh.

CONSUMPTION

0.7-1 kg/m².

PACKAGING

Ultratop Loft W is supplied in 20 kg bags and in 4x5 kg Alupack boxes.

STORAGE

Ultratop Loft W remains stable for 12 months if stored in a dry place.

TECHNICAL DATA (typical values)

In compliance with norm:

EN 13813:2002, CT - C25-F10 - A9-A2_{fi}-s1 - A2-s1-d0**PRODUCT IDENTITY**

Consistency:	fine powder
Colour:	white and natural
Bulk density (kg/m³):	900
Dry solids content (%):	100

APPLICATION DATA (at +23°C - 50% R.H.)

Mixing ratio:	approx. 32-35 parts of water per 100 parts by weight of Ultratop Loft W
Density of mix (kg/m³):	1,600
pH of mix:	11
Application temperature:	from +5°C to +35°C
Workability time:	20 mins.
Setting time:	80 mins.
Set to foot traffic:	3 hours
Waiting time before applying second coat:	6 hours
Waiting time before applying finishing coat:	from 6 to 24 hours

FINAL PERFORMANCE

Performance characteristic	Test method	Requirements according to EN 13813 for cementitious screeds	Performance of product	
Compressive strength:	EN 13892-2	$5 < N/mm^2 < 80$ (28 days)	+ 23°C	
			24 h	8
			7 days	18
			28 days	25
Flexural strength:	EN 13892-2	$1 < N/mm^2 < 50$ (28 days)	+ 23°C	
			24 h	5
			7 days	9
			28 days	12
Abrasion resistance Taber abrasion-meter (H22 disk, 500 g, 200 revs), expressed as loss in weight (g):	ASTM D4060		+ 23°C	
			7 days	0.7
			28 days	0.5
Abrasion resistance (Böhme test):	EN 13892-3	$1.5 < cm^3/50 cm^2 < 22$	+ 23°C	
			28 days	9
Reaction to fire:	EN 13501-1	Value declared by producer	A2 _{fi} -s1 A2-s1-d0	
Castor chair test (type W, n. cycles 25000):	EN 425		Delamination:	no
			Cracks:	no

Ultratop Loft W

The product complies with the conditions of Annex XVII to Regulation (EC) N° 1907/2006 (REACH), item 47.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Ultratop Loft W is not considered as dangerous according to the current regulations regarding the classification of mixtures. It contains special hydraulic binders which, when in contact with sweat or other body fluids, may cause a slightly irritant alkaline reaction. It is recommended to wear protective gloves and goggles and to take the usual precautions for handling chemicals. For further and complete information about the safe use of our product please refer to the latest version of our Material Safety Data Sheet.

PRODUCT FOR PROFESSIONAL USE.

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website www.mapei.com.

ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.



All relevant references for the product are available upon request and from www.mapei.com

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution



BUILDING THE FUTURE

4024-6-2017 (GB)