

# Mapeflex PU20

**Self-levelling,  
two-component  
polyurethane sealant  
for flooring joints  
subject to movements  
of up to 10%**



## WHERE TO USE

- Abrasion-resistant seals in joints in external and internal industrial floors subject to intense traffic.
- Sealing joints in rubber and PVC floors.

## Some application examples

- Sealing expansion joints in concrete floors in car parks and industrial buildings subject to vehicle traffic or where high resistance to chemical agents is required.
- Sealing movement joints in ceramic floors in areas subject to intense traffic such as supermarkets, industrial environments, pavements, pedestrian crossings, arcades, squares and in areas with forklift trucks movement.
- Sealing rubber and PVC floors by filling the joints between each single block or sheet.
- Flexible seals in bases for industrial machinery.
- Flexible seals around pipe-work, waste pipes, manholes, etc.
- Flexible seals of joints in hydraulic applications, such as canals, basins, treatment tanks, swimming pools and water tanks.

## TECHNICAL CHARACTERISTICS

**Mapeflex PU20** is a two-component, self-levelling sealant formed by a polyurethane polymer without free isocyanates (component A) and a special catalyst

(component B), made according to a formula developed in MAPEI's own research laboratories.

When the two components are mixed together, a self-levelling, free-flowing paste with a uniform colour is obtained.

**Mapeflex PU20** may only be applied on horizontal surfaces.

After hardening, which occurs by means of a chemical reaction and without shrinking, **Mapeflex PU20** is flexible, resistant to water and heat, has high resistance to abrasion and bonds well to all materials normally used in the building industry.

**Mapeflex PU20** also has good resistance to chemicals. However, since the product may be subject to a wide range of chemical products and working conditions, preliminary testing must be carried out.

**Mapeflex PU20** is resistant to temperatures from  $-30^{\circ}$  to  $+80^{\circ}\text{C}$ .

## RECOMMENDATIONS

- Do not use on substrates which are subject to rising damp.
- Do not use on surfaces which are damp.
- Do not use on tarmac surfaces which have been laid recently or where the bleeding of oil may be present.
- Do not apply **Mapeflex PU20** if the temperature is lower than  $+10^{\circ}\text{C}$ .

- On vertical surfaces, use **Mapeflex PU30**.

## APPLICATION PROCEDURE

### Mixing

The two components which make up **Mapeflex PU20** are supplied in pre-closed quantities.

- Component A: 94 parts in weight;
- Component B: 6 parts in weight.

The most suitable method for mixing is by means of a low-speed mixer, until a smooth paste with a uniform colour is obtained.

The setting time and pot life of the product depend on the surrounding temperature.

Once mixed, the pot life of the product at +23°C is approximately 45 minutes, but the self-levelling property of the product is at its best during the first 30 minutes. Therefore, we recommend mixing quantities of product which may be applied within this time.

The mixing ratio between the resin (component A) and the catalyst (component B) must be strictly followed.

Do not use partial quantities of the packages, unless the dosage rate of the two components (94 : 6) is measured with high-precision electronic scales.

### Application

All the surfaces to be sealed must be dry, sound and free of dust, crumbly parts, oil, grease and wax.

In order to guarantee that the sealant functions correctly, it must be able to stretch and compress freely once it has been poured into the joints.

Therefore, it is important that **Mapeflex PU20** only bonds to the sides of the joint and not to the bottom, and that the depth of the joint is always less than its width.

To regulate the depth of **Mapeflex PU20** and to avoid it sticking to the bottom of the joint, **Mapefoam** expanded polyurethane must be inserted beforehand in the joint to form a compressible seal.

The size of the joint must be calculated so that, when in service, it moves less than 10% of its total width.

Sealing is normally carried out immediately after mixing **Mapeflex PU20** in a container by pouring it directly into the joint.

In certain cases, masking tape may be required around the joints to avoid rough edges.

### CONSUMPTION

According to the size of the joints, bearing in mind that the density of **Mapeflex PU20** is 1,330 kg/m<sup>2</sup>.

### Cleaning

**Mapeflex PU20** may be removed from surfaces, tools, clothing etc. with toluene or

alcohol before the hardening reaction takes place. After hardening, it may only be removed mechanically or with **Pulicol**.

### COLOURS AVAILABLE

**Mapeflex PU20** is available in anthracite grey.

Special colours are available upon request in quantities of at least 500 kg.

### PACKAGING

**Mapeflex PU20** is available in 10 kg kits (component A 9.4 + component B 0.6) and 5 kg kits (component A 4.7 + component B = 0.3).

### STORAGE

Store the product in a dry place at a temperature between +10°C and +35°C.

### SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Component A of **Mapeflex PU20** irritates if it comes into contact with the eyes or skin.

Component B of **Mapeflex PU20** is corrosive. If it comes into contact with the eyes or skin, it may cause serious injury or burns. If the products come into contact with the eyes or skin, wash off immediately with water and seek medical advice.

The resins contained in **Mapeflex PU20** may cause rashes. Avoid contact with the skin by using protective gloves and goggles.

**Mapeflex PU20** is dangerous for aquatic life: do not dispose the product in the environment.

PRODUCT FOR PROFESSIONAL USE ONLY.

### WARNING

*While the indications and guidelines contained in this data sheet correspond to the company's knowledge and wide experience, they must be considered, under all circumstances, merely as an indication and subject to confirmation only after long-term, practical applications. Therefore, anybody who undertakes to use this product, must ensure beforehand that it is suitable for the intended application and, in all cases, the user is to be held responsible for any consequences deriving from its use.*

**All relevant references  
of the product are available  
upon request**

**TECHNICAL DATA (typical values)****PRODUCT DETAILS**

	<b>component A</b>	<b>component B</b>
<b>Consistency:</b>	fluid paste	liquid
<b>Colour:</b>	anthracite grey	straw-coloured, transparent
<b>Density (g/cm<sup>3</sup>):</b>	1.35	0.92
<b>Dry solids content (%):</b>	96.5	100
<b>Brookfield viscosity at 10 revs (mPa-s):</b>	50,000 # 7	250 # 1
<b>Shelf life:</b>	<b>Mapeflex</b> remains stable for at least 2 years if stored in its original, sealed containers	
<b>Hazard classification according to EC 99/45:</b>	irritant	corrosive, dangerous for the environment. Before using refer to the "Safety instructions for preparation and application" paragraph and the information on the packing and Safety Data Sheet
<b>Customs class:</b>	3909 50 00	

**APPLICATION DATA at 23°C – 50% R.H.**

<b>Mixing ratio:</b>	component A : component B: = 94 : 6
<b>Consistency of the mix:</b>	fluid
<b>Brookfield viscosity of mix at 10 revs (mPa-s):</b>	20,000 # 7
<b>Density of mix (kg/m<sup>3</sup>):</b>	1,330
<b>Pot life of mix (workability time):</b>	45 minutes
<b>Recommended application temperature range:</b>	from +10°C to +30°C
<b>End of setting time:</b>	9 hours
<b>Step-on time:</b>	after 24-36 hours
<b>Waiting time before putting into service:</b>	7 days

**FINAL PERFORMANCES**

<b>Tensile strength (according to DIN 53504-S3a) (N/mm<sup>2</sup>):</b>	1.9
<b>Elongation at breakage (according to DIN 53504-S3a) (%):</b>	190
<b>Shore A hardness:</b>	50
<b>Movement in service (continuous service) (%):</b>	max 10
<b>Abrasion resistance:</b>	excellent
<b>Resistance to humidity:</b>	excellent
<b>Resistance to ageing:</b>	excellent
<b>Resistance to solvents and oil:</b>	good
<b>Resistance to acids and alkalis:</b>	good
<b>In service temperature range:</b>	from -30°C to +80°C
<b>Flexible:</b>	yes

# Mapeflex PU20



**BUILDING THE FUTURE**

## MAPEI GROUP CERTIFIED MANAGEMENT SYSTEMS (Quality, Environment and Safety)



MAPEI S.p.A. - ITALY



MAPEI SUISSE SA

MAPEI Kft. - HUNGARY

MAPEI s.r.o. - CZECH REP.

MAPEI CORP - U.S.A.

MAPEI INC - CANADA

MAPEI FAR EAST Pte Ltd  
MAPEI MALAYSIA SDN BHD

MAPEI ARGENTINA S.A.



MAPEI FRANCE

RESCON MAPEI AS - NORWAY

[www.mapei.com](http://www.mapei.com)